



MORFLEX

COST EFFECTIVE • FLEXURAL STRENGTH • GROUT IN 6 HOURS

Morflex is a premium grade, flexible, cement based tile adhesive. Suitable for both thick and thin bed applications, **Morflex** is polymer modified for bonding all types of tiles to a variety of substrates subject to vibration and thermal movement. **Morflex** installations can usually be grouted after only 6 hours.

SUITABLE SUBSTRATES

- Concrete/Cement Render
- Brickwork/Blockwork (Cement Rendered)
- Fibre Cement Sheets (Primed)
- Plasterboard (Primed)
- Over Morgan Waterproof Membrane

COLOUR	SUITABLE TILES
White	Natural Stone
	Bicottura
INTERIOR/EXTERIOR	Monocottura
Walls	Fully Vitrified
Floors	Porcelain

PRECAUTIONS

Morflex is unsuitable for:

- bonding moisture sensitive green marble
- bonding to MDF board or timber & wax impregnated wood (Our technical advice - sheet with fibre cement boards)
- bonding to substrates subject to constant water immersion such as swimming pools.

SUBSTRATE PREPARATION & EXPANSION JOINTS

All substrates to be tiled must be flat and true, free from oil, dirt, grease or any other contaminants. Very porous substrates should be primed with **Plastinex** (1 part Plastinex mixed with 4 parts water). Incorporate expansion joints in accordance with AS 3958.1 2007.

Concrete : New concrete must be allowed to cure for 6 weeks and should have a wood float finish. Use **Floor Prep** to acid etch an adhesive key into concrete finished with a steel float.

Cement Render : Render to be left with a wood float finish and allowed to cure for 7 days.

Fibre Cement Sheets : Fibre cement sheets must be primed with **Plastinex** (1 part Plastinex mixed with 4 parts water) and all joints must be taped with PVC duct tape and fixed according to the manufacturer's instructions.

Plasterboard : Plasterboard must be fixed as per manufacturer's instructions. Jointing compound must be primed with **Plastinex** (1 part Plastinex mixed with 4 parts water).

OPEN TIME

Morflex has an open time of approximately 30 minutes, which can be shortened to just a few minutes by the action of sun, wind, high temperatures or highly absorbent surfaces. Dampening or priming the substrate prior to tiling prolongs the open time of the adhesive. Tilers need to constantly check that the adhesive has not formed a surface skin and is still fresh to touch. Adhesive with a surface skin must be always removed and discarded.

MIXING & POT LIFE

Add **Morflex** to clean water at a ratio of 20kg to 5 litres of water. Mix the adhesive to a smooth paste free from lumps by using a drill that has a speed lower than 300 rpm, or mix by hand. Slacken the adhesive and re-mix after 5 minutes. **Morflex** has a pot life of approximately 3 hours at 23°C and 50% relative humidity.

**FREE TECHNICAL ADVICE
& MATERIAL SAFETY DATA SHEETS**
Email: info@morganadhesives.com.au
Helpline: (08) 9441 6677 Response within 24 hrs

MORFLEX

COST EFFECTIVE • FLEXURAL STRENGTH • GROUT IN 6 HOURS

COVERAGE

20kgs of **Morflex** will cover approximately 10 square metres with a 6mm notched trowel for walls and approximately 8 square metres with a 10mm notched trowel for floors.

CURE TIME

Morflex cures in approximately 24 hours at 23°C and 50% relative humidity. High density substrates or tiles and temperatures during installation below 10°C will significantly increase the cure time.

CLEAN UP

Remove excess **Morflex** from the grout joints after 30 minutes and clean the tiles with a damp cloth or sponge. Tools and hands can be cleaned with water while the adhesive is still wet.

JOINT GROUTING

Depending on environmental conditions, commence grouting after approximately 6 hours. Use **Regular** or **Superior Grout** for grout joints between 3mm to 6mm. Morgan **Slate & Quarry Grout** should be used for joint sizes between 6mm to 20mm. Use **Aquapoxy**, a three component anti-acid epoxy grout, if the joints are required to have a good chemical resistance. **Grout Add** may also be mixed with **Regular Grout** to impart extra flexibility, reduce porosity and increase water resistance.

JOINT GROUTING PRECAUTIONS

DO NOT use excessive amounts of water during mixing or initial cleaning as this will cause irregular colour finishes and also weaken the grout. **DO NOT** mix the grout with an electric drill above 300 RPM as this can entrap air into the mix causing grout to dry soft and powdery or with unsightly pin holes in the surface. **All grouts should be Damp Cured for 48 hours.** Refer to the Australian Standard AS 3958 Part 1 Section 5.7.3.

SHELF LIFE

Twelve months if stored in a dry & elevated position in the original factory sealed packaging.

PACKAGING

Morflex is available in 20kg bags.

SPECIFICATION CLAUSE

The wall & floor adhesive shall be Morgan **Morflex** - a high performance tile adhesive complying with all relevant Australian & International technical standards.

MORGAN QUALITY POLICY STATEMENT

Morflex is manufactured and distributed to a quality system based on ISO 9001:2000. **Morflex** is guaranteed for 10 years when installed to the guidelines of AS 3958 Part 1 & 2 and in conjunction with written technical information supplied by **Morgan Ceramic Tile Adhesives**.

USER NOTE Although the technical details and recommendations contained in this brochure correspond to the best of our knowledge and experience, all of the above information must, in every case, be taken as merely indicative and subject to confirmation after long term practical applications: for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in any case the user is fully responsible for all consequences deriving from the use of the product.



24 Hanwell Way, Bassendean WA 6054
Ph: 08 9279 8911 • Fx: 08 6278 1152

www.morganadhesives.com.au